PATENT ABSTRACTS OF JAPAN

(11)Publication number:

03-271339

(43) Date of publication of application: 03.12.1991

(51)Int.CI.

C22C 9/00

C22C 1/05 C22C 32/00

(21)Application number: 02-072854

(22)Date of filing:

22.03.1990

(71)Applicant:

HONDA MOTOR CO LTD

(72)Inventor:

KUWABARA MITSUO KOMIYAMA TAKESHI

HIRAI FUMIO

HAYASHI MASAMICHI

(54) CERAMIC-COPPER COMPOSITE BODY AND ITS MANUFACTURE

(57) Abstract:

PURPOSE: To improve the durability and corrosion resistance in a ceramic-copper composite body by mixing Cu, selected metallic elements as an additive and oxides and burning the mixture.

CONSTITUTION: Each powder of Cu as essential components, an additive of at least ≥ two kinds among the group of Cr, Ni, Co, Fe, Ti, V, Mn, Mo, Al, Mg and Si and the oxides of CuO, Cu2O, Ag2O, SnO, etc., are mixed. This mixed powder is compacted and burnt to manufacture a ceramic-copper composite body. The amt. of the additive is regulated to 0.5 to 30wt.%. By the components to be added and the formed ceramic particles, the wettability between the copper alloy as a matrix and the ceramic is improved, by which its interfacial bonding with the matrix can be attained. In this way, the composite body can be densified by sintering.

LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of

rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office